



<b>Product name</b>	:	<b>MoTip Bitumen Based Undercoating</b>	
<b>Article number</b>	:	<b>000007</b>	
<b>Supplier / Producer</b>	:	<b>MOTIP DUPLI B.V.</b>	
		<b>Wolframweg 2</b>	
		<b>NL-8471 XC WOLVEGA</b>	
		<b>Telephone number</b>	<b>+31 561 – 69 44 00</b>
		<b>Telefax number</b>	<b>+31 561 – 69 44 31</b>

---

### Product description

High quality preservative to treat the underside of vehicles.

### Product characteristics

Remains flexible  
Excellent adhesion  
Resistant to weather influences  
Resistant to weak acids and bases  
Excellent corrosion prevention  
Sound-absorbing

### Physical and Chemical Characteristics

Contents	:	500 ml
Colour	:	Black
VOC-content	:	Approximately 70% w/w
Dust dry	:	After approximately 60 minutes

### Usage

**Before use, carefully read the directions on the packaging and act accordingly.**

#### Pre Treatment

Remove loose old lacquer and rust and sand the surface.

#### Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the undercoating in several layers.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

**The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.**